



## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<b>(51) International Patent Classification <sup>6</sup> :</b> <b>C03C 13/00, 13/06</b>	<b>A1</b>	<b>(11) International Publication Number:</b> <b>WO 99/08970</b> <b>(43) International Publication Date:</b> 25 February 1999 (25.02.99)
<b>(21) International Application Number:</b> PCT/FI98/00632 <b>(22) International Filing Date:</b> 17 August 1998 (17.08.98)  <b>(30) Priority Data:</b> 973355                      15 August 1997 (15.08.97)                      FI  <b>(71) Applicant (for all designated States except US):</b> PARTEK PAROC OY AB [FI/FI]; Sörmäisten rantatie 23, FIN-00500 Helsinki (FI).  <b>(72) Inventors; and</b> <b>(75) Inventors/Applicants (for US only):</b> PERANDER, Michael [FI/FI]; Väderkvarnsvägen 10, FIN-21600 Pargas (FI). HAKALA, Jan [FI/FI]; Kardinalgatan 3 L 108, FIN-20380 Åbo (FI).  <b>(74) Agent:</b> OY JALO ANT-WUORINEN AB; Iso Roobertinkatu 4-6 A, FIN-00120 Helsinki (FI).		<b>(81) Designated States:</b> AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, GH, GM, HR, HU, ID, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).  <b>Published</b> <i>With international search report.</i> <i>Before the expiration of the time limit for amending the</i> <i>claims and to be republished in the event of the receipt of</i> <i>amendments.</i>
<b>(54) Title:</b> MINERAL FIBRE  <b>(57) Abstract</b>  The invention concerns a mineral fibre with high temperature resistance and elasticity. The mineral fibre has the following composition in % by weight: SiO <sub>2</sub> 38-47, Al <sub>2</sub> O <sub>3</sub> 16-20, TiO <sub>2</sub> 0-4, MgO 5-15, CaO 14-22, Na <sub>2</sub> O + K <sub>2</sub> O 0-6, iron (FeO + Fe <sub>2</sub> O <sub>3</sub> ) 3-10, P <sub>2</sub> O <sub>5</sub> 0.5-4, other 0-4.		

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon			PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakistan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

## Mineral fibre

The object of the present invention is fiberizable mineral composition as well as  
5 mineral fibres made therefrom, which have a high temperature resistance.

Mineral fibres made by melting and centrifuging of mineral raw materials, such as  
stone, slag or the like, are extensively used for the manufacture of mineral fibre  
mats and blankets, primarily for heat and sound insulation purposes within the  
10 construction industry. In addition to the manufactured mat exhibiting good insulati-  
on properties against heat and sound, in recent times one has started to pay incre-  
asingly more attention to the properties of the mat also from the point of view of  
labour hygiene.

15 A wide range of insulation products are available on the market, which products do  
not only exhibit different heat insulation properties, but also a varying degree of  
temperature resistance. Temperature resistant mineral fibre products are products  
which can resist increased temperatures during prolonged periods of time without  
changing form or dimensions to any higher degree. Such products are thus attracti-  
20 ve from a fire protection point of view.

Conventional glass fibre has a temperature resistance at temperatures up to appr.  
550 °C, whereas the temperature resistance of conventional rock wool is better, up  
to appr. 700 °C. However, there is an interest for products having an even higher  
25 temperature resistance, up to 1100 - 1200 °C, and such products are also available  
on the market.

Such temperature resistant fibre products contain as the main oxides silicium oxide  
SiO<sub>2</sub> and aluminium oxide, Al<sub>2</sub>O<sub>3</sub>, and, in addition, often also an earth alkali  
30 metaloxide, such as calcium oxide, CaO, or magnesium oxide, MgO. In addition,  
such products can contain varying degrees of other oxides, such as titanium oxide,  
TiO<sub>2</sub>, manganese oxide, MnO, boron oxide, B<sub>2</sub>O<sub>3</sub>, zirconium oxide, ZrO<sub>2</sub>, chro-

mium oxide,  $\text{Cr}_2\text{O}_3$ , the alkali oxides sodium and potassium oxide,  $\text{Na}_2\text{O}$ ,  $\text{K}_2\text{O}$ , as well as impurities. As examples of relevant prior art in this respect reference is made, for example, to US 4,461,840 and DE-OS 1 496 662.

- 5 Such temperature resistant fibre products generally contain an increased amount of  $\text{Al}_2\text{O}_3$ , and often relatively high amounts of iron oxide,  $\text{FeO}$  and  $\text{Fe}_2\text{O}_3$ . The presence of iron is due to the fact that many economically attractive raw materials contain iron to higher or lesser degree. However, the presence of aluminium and iron in large amounts makes the fibre brittle and unelastic, which makes the fibre  
10 difficult to handle.

According to the invention it has now been shown that this disadvantage can be eliminated by including phosphorus in the fibre. The addition of phosphorus increases the elasticity and tenacity of the aluminium and iron containing fibre. This  
15 in turn leads to improved handling properties for the fibre products. As the fibre products can be compressed elastically, the need for space, for example, during storing and transport, decreases. As a consequence of the elasticity the product regains its original shape after the release of the compression, and in use well fills all spaces in the building construction. In addition, the tendency for dust formation  
20 decreases due to the decreased fibre brittleness. It has also become evident that it is possible to use an increased concentration of alkalis in such fibres, which can be of advantage in certain applications.

More specifically the invention is directed to a mineral fibre which contains the  
25 following components in % by weight

	SiO <sub>2</sub>	38 - 47
	Al <sub>2</sub> O <sub>3</sub>	16 - 20
	TiO <sub>2</sub>	0 - 4
	MgO	5 - 15
5	CaO	14 - 22
	Na <sub>2</sub> O + K <sub>2</sub> O	0 - 6
	iron (FeO+Fe <sub>2</sub> O <sub>3</sub> )	3 - 10
	P <sub>2</sub> O <sub>5</sub>	0.5 - 4
	other	0 - 4

10

The term "other" components means such possible contaminants which are not of essential importance for the properties of the manufactured fibre.

15 It is known that within the range 0 - appr. 15 % the aluminium oxide concentration is directly proportional to the stability of the fibre in biological solutions, that is, the more aluminium oxide the composition contains, the more stable or poorly soluble the product is. However, this tendency is reversed at a higher concentration so that the solubility of the fibre is increased with the aluminium oxide concentration. Thus, according to the invention a fibre has been obtained which has good heat  
20 resistance, good elasticity and high solubility in biological solutions.

In the above mentioned composition, MgO is preferably 5 - 12 % by weight.

25 According to an advantageous embodiment the invention is directed to a mineral fibre having substantially the following composition in % by weight:

	SiO <sub>2</sub>	40 - 44
	Al <sub>2</sub> O <sub>3</sub>	16 - 20
	TiO <sub>2</sub>	0 - 4
	MgO	8 - 12
5	CaO	16 - 22
	Na <sub>2</sub> O + K <sub>2</sub> O	2 - 5
	iron (FeO+Fe <sub>2</sub> O <sub>3</sub> )	3 - 8
	P <sub>2</sub> O <sub>5</sub>	0.5 - 2
	other	0 - 4

10

The fibre according to the invention is made in a conventional manner by mixing suitable raw materials such as stone, slag, bauxite, dolomite, apatite, anorthosite, glass or different slags and other suitable waste materials in suitable proportions, either as such or as briquettes. The raw materials are then melted, for example in an electrical or cupola furnace, and then made into fibres in any conventional manner, for example by cascade centrifugation of the melt and collecting the fibres on a conveyor.

15

The following examples illustrates the invention without restricting the same.

20

#### Example 1

The following components having the compositions indicated in the following table, were charged in a cupola furnace in the amounts indicated in % by weight.

25

30

	Apatite containing peridotite	Dolomite	Gabbroanorthosite
amount: component: % by weight	32	20	48
5 SiO <sub>2</sub>	45.5	8.0	45.6
Al <sub>2</sub> O <sub>3</sub>	9.9	1.6	30.1
TiO <sub>2</sub>	1.8	0.2	0.2
MgO	11.4	17.8	2.3
CaO	13.7	30.1	16.9
10 Na <sub>2</sub> O + K <sub>2</sub> O	4.5	0.6	1.5
iron	9.7	1.7	2.7
P <sub>2</sub> O <sub>5</sub>	2.2	0.1	0.0
loss on ignition	1.4	39.9	0.7

15

Fibres were made by cascade centrifugation in a conventional manner from the obtained melt, which fibres were collected on a conveyor to form a mineral fibre mat. The mineral fibres had the following composition in % by weight

20	SiO <sub>2</sub>	42.0
	Al <sub>2</sub> O <sub>3</sub>	19.0
	TiO <sub>2</sub>	1.0
	MgO	10.0
	CaO	19.0
25	Na <sub>2</sub> O + K <sub>2</sub> O	3.0
	iron (FeO+Fe <sub>2</sub> O <sub>3</sub> )	4.0
	P <sub>2</sub> O <sub>5</sub>	1.0
	other	1.0.

## Example 2

By choosing suitable raw materials, on the one hand fibres according the invention (fibre A) as well as a comparison fibres (fibre B) were made in the same way as described in the Example 1. The fibres obtained had the following composition in % by weight:

		A	B
10	SiO <sub>2</sub>	42.1	43.9
	Al <sub>2</sub> O <sub>3</sub>	18.7	19.6
	TiO <sub>2</sub>	1.7	0.6
	MgO	10.4	11.3
	CaO	15.8	17.0
15	Na <sub>2</sub> O + K <sub>2</sub> O	2.9	1.7
	iron (FeO+Fe <sub>2</sub> O <sub>3</sub> )	6.8	5.7
	P <sub>2</sub> O <sub>5</sub>	0.8	0.05
	other	0.8.	0.2

20

The fibres A and B contain approximately the same amount of aluminium oxide plus iron oxide, but fibre B contains only an insignificant amount of phosphorus, whereas that of fibre A is within the limits of the invention.

The compressibility of a fibre mat having a density of 27 kg/m<sup>3</sup> made from the fibres A and B respectively, was then measured in the following way. A test specimen (size 30 x 30 cm) of the mat made from the fibres A and B, respectively was compressed in a compressing device between two plates to a thickness corresponding to 20% of its original thickness. The test specimen was kept in the compressed state for 5 minutes, whereafter the compressive force was released and the specimen was allowed to return to its original form for appr. 1 min. The test mat from fibre A according to the invention showed a recovery in this test of 93-94% (after pressure release, the specimen regained 93-94% of its

original thickness) which is a normal value, whereas that of the comparison fibre B was 89-91%, which value is close to the limits of acceptability. Thus the test results show that when the mat made from the fibre A according to the invention has a better compressibility than the reference fibre B.

## Claims

1. Mineral fibre, **characterized** in that it has the following composition in % by weight:

5

SiO<sub>2</sub> 38 - 47

Al<sub>2</sub>O<sub>3</sub> 16 - 20

TiO<sub>2</sub> 0 - 4

MgO 5 - 15

10 CaO 14 - 22

Na<sub>2</sub>O + K<sub>2</sub>O 0 - 6

iron (FeO+Fe<sub>2</sub>O<sub>3</sub>) 3 - 10

P<sub>2</sub>O<sub>5</sub> 0.5 - 4

other 0 - 4

15

2. The mineral fibre according to claim 1, **characterized** in that in the composition, MgO is 5 - 12 % by weight.

3. The mineral fibre according to claim 1 or 2, **characterized** in that it has  
20 substantially the following composition in % by weight:

SiO<sub>2</sub> 40 - 44

Al<sub>2</sub>O<sub>3</sub> 16 - 20

TiO<sub>2</sub> 0 - 4

25 MgO 8 - 12

CaO 16 - 22

Na<sub>2</sub>O + K<sub>2</sub>O 2 - 5

iron (FeO+Fe<sub>2</sub>O<sub>3</sub>) 3 - 8

P<sub>2</sub>O<sub>5</sub> 0.5 - 2

30 other 0 - 4

4. Method for increasing the elasticity and decreasing the brittleness in a mineral fibre, **characterized** in that to a mineral composition containing the oxides  $\text{SiO}_2$ ,  $\text{MgO}$  and  $\text{CaO}$ , and in addition aluminium oxide in an amount of 16-20 % by weight and iron oxides in an amount of 3-10 % by weight, phosphorus is added in the form of a phosphorus containing compound in an amount of 0.5-4 % by weight, calculated as  $\text{P}_2\text{O}_5$ , a melt is formed from the composition, which melt is fiberized to fibres with increased elasticity and decreased brittleness.

5. The method according to claim 4, **characterized** in that to a mineral composition containing in % by weight

	$\text{SiO}_2$	38 - 47
	$\text{Al}_2\text{O}_3$	16 - 20
	$\text{TiO}_2$	0 - 4
15	$\text{MgO}$	5 - 15
	$\text{CaO}$	14 - 22
	$\text{Na}_2\text{O} + \text{K}_2\text{O}$	0 - 6
	iron ( $\text{FeO} + \text{Fe}_2\text{O}_3$ )	3 - 10
	other	0 - 4

20

a phosphorus-containing compound is added in amount of 0.5 - 4 % by weight, calculated as  $\text{P}_2\text{O}_5$ .

6. Product, **characterized** in that it contains a fibre according to claim 1, 2 or 3, or is made according to the method of claim 4 or 5.

7. The product according to claim 6 in the form of a mat or blanket or a tubular bowl, especially for heat and/or sound insulation.

# INTERNATIONAL SEARCH REPORT

International application No.

PCT/FI 98/00632

## A. CLASSIFICATION OF SUBJECT MATTER

**IPC6: C03C 13/00, C03C 13/06**

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

**IPC6: C03C**

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

**SE,DK,FI,NO classes as above**

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 9614454 A2 (ROCKWOOL INTERNATIONAL A/S), 17 May 1996 (17.05.96), claims 4,8  --	1-7
A	WO 9614274 A2 (ROCKWOOL INTERNATIONAL A/S), 17 May 1996 (17.05.96), page 8, line 30 - page 9, line 8, claim 2  --	1-7
A	FR 2662687 A1 (ISOVER SAINT-GOBAIN SOCIETE ANONYME), 6 December 1991 (06.12.91), page 5, line 5 - line 7, claim 1  --	1-7

☒ Further documents are listed in the continuation of Box C.

☒ See patent family annex.

\* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance: the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance: the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search

Date of mailing of the international search report

**11 December 1998**

**14 -12- 1998**

Name and mailing address of the ISA/

Swedish Patent Office

Box 5055, S-102 42 STOCKHOLM

Facsimile No. +46 8 666 02 86

Authorized officer

**Jan Carlerud**

Telephone No. +46 8 782 25 00

**INTERNATIONAL SEARCH REPORT**

International application No.

**PCT/FI 98/00632****C (Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT**

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	GB 2301351 A (ROCKWOOL INTERNATIONAL A/S), 4 December 1996 (04.12.96), page 8, line 16 - page 16, line 26  --	1-7
A	STN International, File CA, Chemical abstracts, volume 81, 24 July 1974, Nitto Boseeki Co. Ltd.: "Glass composition for making glass fiber with high tensile strength", abstract no. 175133, & Japan. Kokai, 4 pp  -- -----	1-7

**INTERNATIONAL SEARCH REPORT**

Information on patent family members

International application No.

PCT/FI 98/00632

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 9614454 A2	17/05/96	AT 169352 T	15/08/98
		AU 3871595 A	31/05/96
		AU 3871695 A	31/05/96
		BE 1009073 A	05/11/96
		BG 101449 A	30/12/97
		BG 101450 A	30/12/97
		CZ 9701404 A	16/09/98
		DE 790962 T	30/04/98
		DE 791087 T	30/04/98
		DE 792843 T	30/04/98
		DE 792844 T	30/04/98
		DE 792845 T	30/04/98
		DE 19581829 T	02/10/97
		DE 19581831 T	02/10/97
		DE 29515168 U	14/03/96
		DE 29521680 U	14/05/98
		DE 69503919 D	00/00/00
		EP 0790962 A	27/08/97
		EP 0791087 A,B	27/08/97
		SE 0791087 T3	
		EP 0792843 A	03/09/97
		EP 0792844 A	03/09/97
		EP 0792845 A	03/09/97
		ES 2111504 T	16/03/98
		ES 2111505 T	16/03/98
		ES 2111506 T	16/03/98
		ES 2111507 T	16/03/98
		ES 2111508 T	16/03/98
		FI 972515 A	13/08/97
		FI 972516 A	13/08/97
		FR 2726548 A	10/05/96
		GB 9422468 D	00/00/00
		GR 98300009 T	31/03/98
		GR 98300010 T	31/03/98
		GR 98300011 T	31/03/98
		GR 98300012 T	31/03/98
		GR 98300013 T	31/03/98
		HU 77859 A	28/08/98
		HU 77860 A	28/08/98
		JP 10509774 T	22/09/98
		NL 1001607 A,C	00/00/00
		PL 320344 A	29/09/97
		PL 320363 A	29/09/97
		SK 55097 A	05/11/97
		SK 55197 A	08/10/97
		WO 9614274 A	17/05/96
		GB 9424126 D	00/00/00
		GB 9424127 D	00/00/00
		AU 1956595 A	30/10/95
		BG 100893 A	30/12/97
		BR 9507310 A	07/10/97
		DE 69502721 D	00/00/00
		EP 0764183 A,B	26/03/97
		SE 0764183 T3	

### Information on patent family members

03/11/98

International application No.

PCT/FI 98/00632

Form PCT/ISA/210 (patent family annex) (July 1992)

## INTERNATIONAL SEARCH REPORT

Information on patent family members

03/11/98

International application No.

PCT/FI 98/00632

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 9614274 A2	17/05/96	AT 169352 T	15/08/98
		AU 3871595 A	31/05/96
		AU 3871695 A	31/05/96
		BE 1009073 A	05/11/96
		BG 101449 A	30/12/97
		BG 101450 A	30/12/97
		CZ 9701404 A	16/09/98
		DE 790962 T	30/04/98
		DE 791087 T	30/04/98
		DE 792843 T	30/04/98
		DE 792844 T	30/04/98
		DE 792845 T	30/04/98
		DE 19581829 T	02/10/97
		DE 19581831 T	02/10/97
		DE 29515168 U	14/03/96
		DE 29521680 U	14/05/98
		DE 69503919 D	00/00/00
		EP 0790962 A	27/08/97
		EP 0791087 A,B	27/08/97
		SE 0791087 T3	
		EP 0792843 A	03/09/97
		EP 0792844 A	03/09/97
		EP 0792845 A	03/09/97
		ES 2111504 T	16/03/98
		ES 2111505 T	16/03/98
		ES 2111506 T	16/03/98
		ES 2111507 T	16/03/98
		ES 2111508 T	16/03/98
		FI 972515 A	13/08/97
		FI 972516 A	13/08/97
		FR 2726548 A	10/05/96
		GB 9422468 D	00/00/00
		GR 98300009 T	31/03/98
		GR 98300010 T	31/03/98
		GR 98300011 T	31/03/98
		GR 98300012 T	31/03/98
		GR 98300013 T	31/03/98
		HU 77859 A	28/08/98
		HU 77860 A	28/08/98
		JP 10509774 T	22/09/98
		NL 1001607 A,C	00/00/00
		PL 320344 A	29/09/97
		PL 320363 A	29/09/97
		SK 55097 A	05/11/97
		SK 55197 A	08/10/97
		WO 9614454 A	17/05/96
		GB 9424126 D	00/00/00
		GB 9424127 D	00/00/00
		AU 1956595 A	30/10/95
		BG 100893 A	30/12/97
		BR 9507310 A	07/10/97
		DE 69502721 D	00/00/00
		EP 0764183 A,B	26/03/97
		SE 0764183 T3	

**INTERNATIONAL SEARCH REPORT**

Information on patent family members

03/11/98

International application No.

PCT/FI 98/00632

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
		FI 964014 A	07/10/96
		GB 9500667 D	00/00/00
		JP 10502206 T	24/02/98
		NO 964255 A	03/12/96
		PL 316674 A	03/02/97
		SK 127996 A	09/04/97
		US 5785912 A	28/07/98
FR 2662687 A1	06/12/91	US RE35557 E	08/07/97
GB 2301351 A	04/12/96	GB 9516759 D	00/00/00